



AFB™ 6164W


Avery Dennison AFB™ 6164W is white acrylic double coated foam tape with multipurpose acrylic adhesive on both sides. This firm foam adhesive offers strong lamination properties and good weather and environmental resistance. An additional layer of adhesive offers resistance of migration toward plasticizer in vinyl substrates. Suitable for a wide range of applications, including large domestic appliances, nameplate or sign bonding, and control panel mounting

FEATURES:

- · Foam tape with viscoelastic acrylic foam carrier
- · Closed cell structure
- Acrylic adhesive system
- · Easy release paper liner

BENEFITS:

- High adhesion combined with good shear absorbs shock and distributes stress evenly
- · Good moisture, UV and high temperature resistance
- · Uniform bonding performance
- Can help eliminate the need for mechanical fasteners, drilling or grinding and related clean-up for certain applications



CONSTRUCTION:

Liner:

Polyethylene Coated White Paper

Adhesive:

Acrylic

Carrier:

White Acrylic Foam Core

Adhesive:

Acrylic





AFB™ 6164W

Adhesive Properties:		Typical Values		
hickness	ASTM D-3652	US Mils	MM's	Micron's (µm)
Liner:		6.3	0.16	160
Carrier & Adhesive:		25.2	0.64	640
otal Caliper:		31.5	0.80	800
PEEL ADHESION	Test Method(s): PSTC-101	, ASTM D-3330		
	(305 mm / min)			
Substrate		Lbf / In		N / 100 mm
SS	20 min dwell	9.6		168
Polycarbonate	20 min dwell	5.5		96
2 mil PET 90° 12 in /min ((305 mm / min)			
SS	72 hr dwell	15.1		264
Polycarbonate	72 hr dwell	13.7		240
DYNAMIC SHEAR	Test Method(s): ASTM D-1	002	I	
2 mil PET 0.5 in /min (12.7 m	nm / min)	11.6/12		kPa
Substrate	70 has describe	Lbf / In ² 120.4		830
Liner	72 hr dwell	120.4		830
NORMAL TENSILE	Test Method(s): ASTM D-8	97		
Aluminum 2 in / min (50.8 mr				
Substrate		Lbf / In²		kPa
Aluminum	72 hr dwell	117.5		810
STATIC SHEAR 2 mil PET 1" sq (6.5 cm2)	Test Method(s): PSTC-101	, ASTM D-3330		
2 mil PET 1" sq (6.5 cm2) Substrate	500 g	Min to Fail		
SS	@ 90°C	> 10,000		
TEMPERATURES		°F		° C
Long Term Temp (10,000 mins)		194 ° F		90 ° C
Short Term Temp (240 mins)		302 ° F		150 ° C
1 \ ' /				-

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.

Europe



Performance Tapes Asia Pacific Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059 South America Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America North America 250 Chester Street Painesville, Ohio 44077 USA

Phone: +1 866-462-8379 Fax: +1 888-358-4469