



# FM 2132

Avery Dennison<sup>™</sup> FM 2132 is a 36 mil double coated white polyethylene foam with a high shear rubber adhesive. It bonds to a wide variety of low surface energy materials and features high shear strength and the ability to fill gaps. FM 2132 is commonly used in general industrial foam applications.

## **FEATURES**

- Double coated tape construction
- High shear rubber adhesive
- Polyethylene foam carrier
- Super calendered kraft release liner

### BENEFITS

- Dimensional stability and good die cutting characteristics
- Strong bond to a wide variety of low surface energy materials
- High shear and high temperature resistance
- Gap filling properties and good conformability
- High tensile strength and tear resistance with excellent die cutting performance
- Two-year warranty



## CONSTRUCTION:

Liner: 60# White Kraft Adhesive 1: Rubber Carrier: Polyethylene Foam Adhesive 2: Rubber





| Adhesive Properties:            |                    | Typical Values |      |               |  |
|---------------------------------|--------------------|----------------|------|---------------|--|
| Thickness                       | ASTM D3652         | US Mils        | MM's | Micron's (µm) |  |
| iner                            |                    | 3.5            | 0.09 | 89            |  |
| Adhesive 1 - Liner              |                    | 2.5            | 0.06 | 64            |  |
| Carrier                         |                    | 31.0           | 0.79 | 787           |  |
| Adhesive 2 - Unwind             |                    | 2.5            | 0.06 | 64            |  |
|                                 |                    |                |      |               |  |
| Total Caliper without Lir       | ner:               | 36.0           | 0.91 | 914           |  |
| Total Caliper:                  |                    | 39.5           | 1.00 | 1003          |  |
|                                 |                    |                |      | •             |  |
| Peel Adhesion                   | ASTM D3330         |                |      |               |  |
| 80° 12 in (300 mm) m            | iin @ Room Temp    |                |      |               |  |
| Substrate                       |                    | Lbf / in       |      | N / Meter     |  |
| SS                              | Liner 72 hr dwell  | 7.5            |      | 1,321         |  |
|                                 |                    |                |      | ,             |  |
|                                 |                    | T              |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 | Unwind             | 7.5            |      | 1,321         |  |
|                                 |                    |                |      | .,            |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
| р                               | Liner 72 hr dwell  | 7.5            |      | 1,321         |  |
|                                 |                    | 1.5            |      | 1,021         |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 | Unwind             | 7.5            |      | 1,321         |  |
|                                 | OTWING             | 1.5            |      | 1,521         |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    | I.             |      |               |  |
| Loop Tack                       | ASTM D6195         |                |      |               |  |
| 180° 32 in (508 mm) / 1         |                    |                |      |               |  |
| Substrate                       | Carteen renip      | Lbf / in       |      | N / Meter     |  |
| SS                              | Liner Initial      | 12.0           |      | 2,113         |  |
|                                 |                    |                |      | _,            |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                | I    |               |  |
| Static Shear                    | ASTM D3654         |                |      |               |  |
|                                 | 1000 g @ Room Temp |                |      |               |  |
| Substrate                       |                    | Min to Fail    |      |               |  |
| SS                              | Liner 24 hr dwell  | > 10,000       |      |               |  |
|                                 |                    | ~ 10,000       |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    |                |      |               |  |
|                                 |                    | ~ =            |      |               |  |
| TEMPERATURES                    |                    | ° F            | 1    | 0 C           |  |
| Minimum Application Temperature |                    | 50° F          |      | 10° C         |  |
| Minimum Service Temp            |                    | -40° F         |      | -40° C        |  |
| Maximum Service Temperature     |                    | 175° F         |      | 80° C         |  |

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

## **APPLICATION TECHNIQUES**

It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil

• Bond strength is dependent upon the amount of adhesive-to-surface contact developed

Performance

Tapes

· Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

#### STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335 Phone: +86 512 57155051 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379 Fax: +1 888-358-4469

